

# PRV

PATENT- OCH REGISTRERINGSVERKET  
Patentavdelningen

BEST AVAILABLE COPY

PCT/EP02/14655

10/500188

REC'D 09 MAY 2003

WIPO

PCT

## Intyg Certificate

Härmed intygas att bifogade kopior överensstämmer med de handlingar som ursprungligen ingivits till Patent- och registreringsverket i nedannämnda ansökan.

This is to certify that the annexed is a true copy of the documents as originally filed with the Patent- and Registration Office in connection with the following patent application.

(71) Sökande Jan Otto Solem, Stetten CH  
Applicant (s) Per Ola Kimblad, Lund SE

(21) Patentansökningsnummer 0200073-5  
Patent application number

(86) Ingivningsdatum 2002-01-11  
Date of filing

Stockholm, 2003-01-28

För Patent- och registreringsverket  
For the Patent- and Registration Office

*Christina Vängborg*  
Christina Vängborg

Avgift  
Fee 170:-

EPO - DG 1

28. 04. 2003

(49)

**PRIORITY DOCUMENT**  
SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH  
RULE 17.1(a) OR (b)

**PATENT- OCH  
REGISTRERINGSVERKET  
SWEDEN**

Postadress/Adress  
Box 5055  
S-102 42 STOCKHOLM

Telefon/Phone  
+46 8 782 25 00  
Vx 08-782 25 00

Telex  
17978  
PATOREG S

Telefax  
+46 8 666 02 86  
08-666 02 86

AWAPATENT AB

JAN OTTO SOLEN  
PER OLA KIMBLADKontor/Handläggare  
Helsingborg/Magnus Hjerpe/SG

Ansökningsnr

Vår referens  
SE-2014193

1

DELAYED MEMORY DEVICETechnical field of the invention

The present invention relates to a medical device for providing a change of shape in a part of the body of an organism. The invention further relates to a device  
5 and a method for reshaping a body vessel, and a device and a method for restraining growth of a body organ of an organism.

Background of the Invention

At present the treatment of mitral annulus dilata-  
10 tion and other mitral insufficiencies consists of either repair or mitral valve replacements. Both methods require open-heart surgery, by the use of total cardiopulmonary by-pass, aortic cross-clamping and cardioplegic arrest. To certain groups of patients, open-heart surgery is  
15 particularly hazardous and therefore a less invasive method for repair of mitral insufficiency is desired.

Such a less invasive method is proposed in U.S. Patent No. 6,210,432, which describes a method for treatment of mitral insufficiency without the need for  
20 cardiopulmonary by-pass and opening of the chest and heart. The method uses a device comprising an elongate body having such dimensions as to be insertable into the coronary sinus, which is a vein that substantially encircles the mitral orifice and annulus and drains blood  
25 from the myocardium to the right atrium. The elongate body has two states, in a first of which the elongate body has a shape that is adaptable to the shape of the coronary sinus, and to the second of which the elongate body is transferable from said first state assuming a  
30 reduced radius of curvature. Consequently, the radius of curvature of the coronary sinus is reduced. Due to the

coronary sinus encircling the mitral annulus, the radius of curvature as well as the circumference of the mitral annulus are reduced. Thus, the described method takes advantage of the position of the coronary sinus being  
5 close to the mitral annulus, which makes repair possible by the use of current catheter-guided techniques.

According to one method described in U.S. Patent No. 6,210,432, a device comprising an elongate stent is used. The elongate stent includes hooks which are  
10 arranged to dig into the walls of the coronary sinus, by means of the surgeon retracting a cover sheet from the stent, in order to fix the position of the stent in the coronary sinus. A stabilizing instrument is used for keeping the elongate stent in its first state and then,  
15 after the hooks have dug into the walls, releasing it to its second state assuming a reduced radius of curvature. However, the position fixation of the elongate stent in the coronary sinus by means of the hooks might be insufficient, so that the sudden release of the  
20 contraction of the elongate stent dislocates it. This dislocation of the device might result in unsatisfactory reduction of the circumference of the mitral annulus.

According to an alternative method described in U.S. Patent No. 6,210,432 the device comprises three stent  
25 sections that are positioned in the coronary sinus and connected by wires. The wires may be manoeuvred from outside the vein system such that the distances between the adjacent stent sections are reduced. Also with this method there is a risk of dislocation of the device,  
30 since the surgeon might accidentally move insufficiently fixed stent sections out of proper position while manipulating them from outside the vein system.

#### Summary of the Invention

An object of the present invention is to provide a  
35 more secure fixation of a medical device for providing a change of shape in a part of the body of an organism.

A particular object of the invention is to provide a more secure fixation of a device for reshaping a body vessel, as described above.

These and other objects are achieved by a device as  
5 defined in anyone of claims 1, 17, 26, and 31 and by a method as defined in claim 42.

More particularly, according to one aspect of the present invention, a medical device being insertable into the body of an organism comprises a member having a  
10 preferred state of shape towards which the member by means of inherent forces strive when being in a non-preferred state of shape, and a delay means having a weakenable inherent stiffness to hold the member in the non-preferred state of shape a period of time after the  
15 device is inserted into the body of the organism. The member is by means of said inherent forces arranged to provide a change of shape in a part of the body of an organism, whereas the delay means is arranged to delay the change of shape a period of time. The time period is  
20 determined by how fast the weakening of said inherent stiffness proceeds. By delaying the change of shape this way, the device is allowed to heal on to body tissue of the organism before a change of shape of the device occurs. Which parts of the device that become fixed by  
25 the healing process can be determined by means of the design of the device. The normal healing process that occurs in every living organism is thus allowed to provide a well-established fixation of the device. Hence, the present invention provides a more secure fixation of  
30 a medical device for providing a change of shape in a part of the body of an organism.

In a preferred embodiment of the invention, said delay means holds said member in a non-preferred state of shape by counteracting the inherent forces of the member.  
35 Thus, the delay means is arranged to apply force to the member by means of the inherent stiffness, in order to counteract the inherent shape-changing forces of the

member and thereby restrain the member from changing its shape.

Preferably, said delay means holds said member in a non-preferred state of shape while the inherent stiffness of the delay means overcomes the inherent forces of the member. That is, there is an equilibrium between the inherent forces of the member and the inherent stiffness of the delay means, and when the stiffness of the delay means no longer is strong enough to balance the inherent forces of the member the change of shape will occur.

In another preferred embodiment of the invention, said delay means comprises a decomposable material. In this way, the inherent stiffness of the delay means is allowed to weaken simply as a result of the decomposable material of the delay means being decomposed.

Preferably, said delay means comprises a resorbable material. A resorbable material is such a material that when it is inserted into the body of an organism, it will be resorbed by the body by means of enzymatic processes and also by active absorption by the cells in the blood and tissue cells of the body. Thus, the resorbable material of the delay means will advantageously be decomposed and vanish from the device by time, without leaving any major waste products in the body.

In another preferred embodiment, said member comprises an elastic material. An elastic material can in a simple way be forced to adopt a non-preferred shape.

In yet another preferred embodiment, said member comprises a material having superelasticity properties. Superelasticity properties means that the material may be deformed and in the deformed state the material will use its superelasticity forces to return to its preferred shape. These superelasticity forces constitutes thus advantageously at least part of said inherent forces providing said strive towards said preferred state of shape of the member.

Preferably, said member comprises a shape memory material. A shape memory material is such a material that has two different forms, one at lower temperatures and another at higher temperatures. At the lower  
5 temperatures, e.g. below 30°C, the material is elastic and may be introduced into the body. At the higher temperatures, the material is still elastic but becomes also superelastic and assumes its preferred original shape unless the transformation to this original shape is  
10 obstructed by external stress to the material. The use of a shape memory material in the member is advantageous i.a. because then one can easily provide the device with said delay means while the member, at a lower temperature outside the body, assumes a shape corresponding to said  
15 non-preferred state of shape inside the body.

According to another aspect of the present invention, a medical device for providing a change of shape in a part of the body of an organism comprises a first set of forces working towards a change of shape of  
20 the device, and a second set of forces working for preserving a present shape of the device and thereby counteracting said first set of forces. Said first and said second sets of forces are each inherent in a solid material of the device, and the forces of said second set  
25 of forces are arranged to decrease as a result of said solid material interacting chemically with said part of the body. As a result of the chemical interaction between the solid material of the device and the surrounding body, the forces of the second set of forces decrease and  
30 thus allow the device to provide said change of shape after a while, when parts of the device have become fixed in the body by a healing process. An advantage of the present invention, except that it provides a more secure fixation, is that there is no need for a stabilizing  
35 surgical instrument for keeping a present shape of the device during operation, since the shape is preserved by

means of said second set of forces being inherent in the device itself.

Preferably said second set of forces is inherent in a decomposable material as mentioned above.

5 Said forces of said second set of forces are preferably arranged to decrease as a result of said solid material being decomposed by said part of the body.

In a preferred embodiment of the invention, said second set of forces is inherent in a resorbable material  
10 as described above.

Preferably, said forces of said second set of forces are arranged to decrease as a result of said solid material being resorbed by said part of the body.

In another preferred embodiment, said first set of  
15 forces is inherent in an elastic material.

Preferably, said first set of forces is inherent in a material having superelasticity properties as described above.

Said first set of forces is preferably inherent in a  
20 shape memory material as also described above.

In one embodiment of the invention, said first set of forces is inherent in a shape memory metal.

In an alternative embodiment of the invention, said first set of forces is inherent in a shape memory  
25 polymer.

The device is in one embodiment arranged to contract into a new shape as a result of said second set of forces being decreased.

In an alternative embodiment, the device is arranged  
30 to expand into a new shape as a result of said second set of forces being decreased.

The device could be arranged to change its shape in one dimension only, but it could also be arranged to change its shape in two dimensions, or even in three  
35 dimensions.

According to yet another aspect of the present invention, a medical device being insertable into the

body of an organism comprises a member having a preferred state of shape and having a tendency to transfer its shape towards said preferred state of shape when being in a non-preferred state of shape. The device further  
5 comprises a resorbable means being arranged to hold the member in the non-preferred state of shape and to delay the transfer when the device is inserted into the body of the organism by counteracting said transfer during  
10 resorption of the resorbable means by the surrounding body of the organism. The resorption of the resorbable means by the surrounding body makes the resorbable means gradually vanish. Thus, after some period of time when parts of the device have grown on to body tissue, there is nothing left to hold the member in the non-preferred  
15 state of shape whereby said transfer is released.

Also according to this aspect of the invention, said member preferably comprises an elastic material.

Preferably, said member comprises a material having superelasticity properties.

20 It is also preferred that said member comprises a shape memory material.

According to a particular aspect of the present invention, a device for reshaping a body vessel being elongate and having such dimensions as to be insertable  
25 into the vessel and having two states, in a first of which the device has a shape that is adaptable to the shape of the vessel, and to the second of which the device is transferable from said first state. The device further comprises a fixing means for fixing the ends of  
30 the device within the vessel, when the device is first positioned therein, a member for transferring the device to the second state by reshaping it, and a resorbable means for delaying said reshaping until the ends of the device are fixed by keeping said device in said first  
35 state until the resorbable means is resorbed. By allowing the ends of the device to heal on to the walls of the vessel, e.g. the coronary sinus, by means of said fixing



means, before said reshaping of the device occurs, the present invention provides a more secure fixation of a device for reshaping a body vessel.

Preferably, said resorbable means comprises a  
5 resorbable sheath being arranged to enclose said member. This is advantageous since with the shape of a sheath the resorbable means is both easy to manufacture and easy to put on the member.

In another preferred embodiment of the invention,  
10 said fixing means is arranged to expand against the wall of the vessel when first positioned therein. This expansion against the wall of the vessel initiates and contributes to the fixing of the ends of the device, thus enabling a rigid fixing.

In yet another preferred embodiment of the  
15 invention, said fixing means is arranged to grow into the wall of the vessel. By taking advantage of the healing process in the tissue of the vessel wall the fixing means can be fixed effectively. This can be facilitated by an  
20 expansion against the wall of the vessel as mentioned above.

In a preferred embodiment, said fixing means comprises a self-expandable stent at each end of the device.

25 According to another preferred embodiment, said member comprises a shape memory material providing said reshaping of the device.

Preferably, said reshaping of said device comprises shortening of said device.

30 In another preferred embodiment, said device is used for treatment of mitral annulus dilatation. Since the device can be inserted into a body vessel using catheter-guided techniques, the use of this device for treatment of mitral annulus dilatation is advantageous compared to  
35 open-heart surgery, which is the present procedure for repairing or replacing the mitral valve.

In yet another preferred embodiment, said vessel is the coronary sinus. The coronary sinus encircles the mitral orifice and annulus. Therefore, a reshaping of this vein also has a compressing effect on the mitral annulus.

Preferably, said reshaping of said device is used for reducing the radius of curvature of the coronary sinus. Hence, the radius of curvature as well as the circumference of the mitral annulus are also reduced.

According to the invention, a method for reshaping a body vessel comprises the steps of inserting a device into the vessel, fixing the ends of the device within the vessel, reshaping the device, and delaying said reshaping by a resorbable means so that the step of fixing the ends of the device is performed before the step of reshaping the device.

In a preferred embodiment, said step of fixing the ends of the device comprises providing a growth of the ends into the wall of the vessel.

The basic inventive idea, that reshaping of an implantable device may be delayed by means of a delay means being comprised in the device itself, opens up for new possibilities within many medical applications.

The present invention could be used for instance when a delayed expansion of a stent is desired. The stent could then preferably be crimped to a small diameter by means of a resorbable suture or, alternatively, a resorbable film. The film or thread would slowly be eaten away and the shape-changing forces may be released after the desired delay which is programmed in the properties of the resorbable restraining material. Such a stent might be used inside vessels, the trachea, the biliary tract or any other hollow structure in the human or animal body.

The invention would also be useful where openings of human, or animal, organs or other structures need to be opened or closed slowly. For instance, when an opening

between the left and right side of the heart is present an immediate closure of the opening could be dangerous, whereas a slower closure would be tolerant.

Within many medical areas, the present invention  
5 would be useful when a continuous long-term effect of shape-changing forces is desired. One such application would be a device designed to shorten or lengthen a human or animal structure in one or more dimensions. The device according to the invention would then have time to heal  
10 into the body structure before shape-changing forces are released and force the body structure to slowly change its shape.

This could for example be useful in the area of orthopaedics for lengthening of a bone structure.

15 For orthodontic treatment the described invention would be useful when it comes to tooth-regulation and lengthening of the maxilla and/or mandibula, i.e. the upper and lower jaws.

In plastic surgery an extra growth of skin area is  
20 often used to cover skin defects. Using the present invention a slow growth of skin area would be augmented.

An example within the area of urology surgery is lengthening of a penis. In this case a device made of three segments could be designed, where the distal ends  
25 of the device first are allowed to grow into the tissue. After fixation of the two ends of the device in the penis tissue, the mid portion which temporarily has been restrained by means of a resorbable material as described above will be released and the mid portion of the device  
30 will grow in length. One specific capacity of a human or animal body is to allow slow deformation of organs or tissues by compensatory tissue adaptation. A penis would therefore grow slowly to a predetermined length.

By means of the present invention, a sequential  
35 effect of shape-changing forces could also be provided, i.e. change of shape could occur in two or several steps as a result of resorbable material releasing the shape-

changing forces in predetermined steps. In each step, a part or parts of a device could first heal into a body structure and secondly the desired shape-changing effects could be released.

5 As seen from the examples above, a substantial advantage with the present invention is that a change of shape is allowed to be made slowly so that body tissue have time to adapt.

10 Other medical applications of particular interest, which could be improved by using the present invention, are treatment of pathological heart growth and treatment of pathological alveolar sac growth. Some background of these two diseases will be given next.

15 Dilated cardiomyopathy (DCM) and ischemic heart disease (IHD) are common reasons for heart failure (HF). Heart failure in its terminal status is a deadly disease, it is by far the most common cause of death in most countries, developed and undeveloped. Progressive HF when it is deteriorating results in a growth in the diameters  
20 of the heart ventricles thus resulting in a general heart growth. The growth in heart size by dilatation initiated by myocardial pathology creates itself by its increase in heart diameter a pathology of its own, in the way of functional disorders.

25 Dr. Randas Batista implemented a surgical treatment for this disease by resecting big parts of the left ventricle (LV) with or without repair of the mitral valve. The long time results were, however, dismal since the LV tends to dilate again a second time despite of  
30 having been reduced in size by surgery.

Supporting the LV and preventing progressive LV dilatation in HF actively by means of wrapping the heart with living skeletal muscle from the back of the patient, stimulated by pacemaker was introduced by Dr. Carpentier  
35 in the eighties. The method never proved to be effective.

More recently, methods of restraining the heart from growing have been introduced by Acorn Cardiovascular,

Inc, St. Paul, MN, USA. They are supporting the heart by means of a polyester mesh sutured to the surface of the heart after exposing the heart by splitting the sternum and opening the pericardium.

5 Even reducing the LV diameter by force, using wires that transverse the LV cavity and subsequent fixation has been introduced by Myocor, Maple Grove, MN 55311, USA.

Chronic obstructive pulmonary disease (COPD) is an umbrella term used to describe airflow obstruction that  
10 is associated mainly with emphysema and chronic bronchitis. COPD is the fourth leading cause of death in the U.S. in 1998, according to National Center for Health Statistics, Report of Final Morbidity Statistics, 1998.

Emphysema causes irreversible lung damage by  
15 weakening and breaking the air sacs within the lungs. Further, sick air sacs sometimes grow unrestrainedly and repress smaller air sacs, resulting in lack of oxygen and by time death. This disease is hard to treat. At present, surgical treatment of dilated air sacs involves cutting  
20 them away, but this treatment gives no long-term effect since a new air sac will soon start to grow.

All these known methods for treatment of pathological heart growth and said known method for treatment of alveolar sac growth require, whether they  
25 are effective or not, open heart surgery which, as mentioned before, is particularly hazardous to certain groups of patients. Therefore less invasive methods for treatment of pathological heart growth and alveolar sac growth are desired as well.

30 It is an object of the present invention to also provide less invasive treatments of pathological growth of body organs, by which treatments more long-term effects can be achieved.

A particular object of the invention is to provide  
35 less invasive treatments of pathological heart growth and alveolar sac growth.

These further objects are achieved by a device as defined in claim 50 and by a method as defined in claim 53.

5 More particularly, according to a further aspect of the present invention, a device for restraining growth of a body organ of an organism is implantable into the body of the organism and comprises an elastic contractable member being arranged to enclose said body organ, and a  
10 resorbable means being arranged to delay contraction of the contractable member when the device is implanted in the body of the organism by counteracting the contraction during resorption of the resorbable means by the surrounding body of the organism.

15 A basic advantage of the device according to the invention is that the device, since said contractable member is elastic, can be inserted into the body using catheter-guided techniques. Hence, less invasive treatments can be provided.

20 Another advantage, which comes both from the elasticity and the delayed contraction, is that the device can be inserted by means of catheter-guided techniques even if said contractable member comprises a large area. This is due to that the substantially elastic device at the insertion can be rolled up on a catheter  
25 and then be unfolded to enclose said organ.

After a period of time after the surgical operation, the device will start to contract as a result of the resorbable means being resorbed. The contraction will then make the device enclose the organ tight and apply a  
30 restraining force which holds back the growth of the organ. Since the implanted device applies a continuous restraining force to the organ, more long-term effects can be achieved in treatment of growing body organs. Note that if the contraction of the device would not have been  
35 delayed, it would have been very difficult to roll up the device on a catheter and then unfold it round the organ.

Preferably, said contractable member comprises a shape memory material.

According to the invention, a method for restraining growth of a body organ of an organism comprises the steps  
 5 of inserting a restraining device into the body of the organism, enclosing the body organ with the restraining device, compressing said restraining device by means of a contractable member of said restraining device, and delaying said compression by a resorbable means.

10 This inventive method could be used not only for treatment of pathological heart growth and alveolar sac growth, but also for treatment of bullous emphysema and for treatment of other body organs growing pathological-ly.

15 As already seen, the number of advantages of the inventive device is large, of which a few are mentioned next. The present invention allows:

1. less invasive surgical treatments;
2. devices that are properly fixed inside the body by  
 20 means of parts healing into the body tissue;
3. devices to be designed that have multiple purposes;
4. eliminating stabilizing surgical instruments for keeping a present shape of the device during operation;
- 25 5. engineering to decide when a shape-changing action by the device is to take place in the body;
6. a change of shape to be made slowly so that body tissue have time to adapt.

It should be understood that many modifications are  
 30 possible within the spirit and scope of the invention, which is only limited by the enclosed claims. A few applications of the invention are mentioned above, of which some are further described by way of illustration only next in the detailed description. However, many  
 35 other medical areas where the invention might be used will become apparent to those skilled in the art.

Brief Description of the Drawings

The invention will now be described in more detail with reference to the accompanying drawings, in which

5 Figs 1-4 are schematic views of the structure and the operation of an embodiment of a device according to the invention, illustrating the principle of delayed shortening;

10 Figs 5-8 are schematic views of the structure and the operation of another embodiment of a device according to the invention, illustrating the principle of delayed elongation;

Fig. 9 is a schematic view of another embodiment of a device according to the invention being an alternative to the embodiment shown in Fig. 7;

15 Figs 10 and 11 schematically illustrate another embodiment of a device according to the invention, shown in a first state and a second shortened state, respectively;

20 Figs 12 and 13 schematically illustrate another embodiment of a device according to the invention, shown in a first state and a second elongated state, respectively;

25 Fig. 14 is a schematic view of yet another embodiment of a device according to the invention, shown in a first state;

30 Fig. 15a is a schematic view of another embodiment of a device according to the invention being an alternative to the embodiment shown in Fig. 14 and being shown in a first state;

Fig. 15b is a schematic view of a device according to Fig. 15a, illustrating the structure of a part of the device;

35 Fig. 16 is a schematic view illustrating the second state of a device according to Fig. 14 or 15b;

Figs 17 and 18 are schematic views illustrating another embodiment of a device according to the



invention, shown in a first state and a second state, respectively;

Fig. 19 is a schematic perspective view of a device for two-dimensional contraction according to the invention;

Fig. 20 is a schematic perspective view of another device for two-dimensional contraction according to the invention;

Figs 21 and 22 schematically illustrate an embodiment of a device according to the invention for treatment of mitral annulus dilatation, shown in a first state and a second shortened state, respectively;

Figs 23, 24 and 25 are schematic views illustrating the positioning, the fixing and the shortening respectively, of a device according to Fig. 21 when used in the coronary sinus;

Fig. 26 is a schematic perspective view illustrating a part of one possible arrangement of a device according to the invention presenting a reshapable area;

Figs 27-30 are schematic views illustrating the positioning and the contraction of an embodiment of the device according to the invention for treatment of pathological heart growth;

Figs 31 and 32 are schematic views illustrating the positioning of an embodiment of the device according to the invention for treatment of chronic obstructive pulmonary disease.

#### Detailed Description of Preferred Embodiments

Figs 1 to 4 show the principle of delayed shortening according to the invention.

In Fig. 1, a shape-changing member 1, here in the form of a thread 1, made of or at least in part including a shape memory material is shown having a curved shape. This shape is the original shape that the shape-changing member 1 "remembers" and will assume when the temperature thereof passes a certain threshold, e.g. exceeds 30°C.

Fig. 2 shows the shape-changing member 1 of Fig. 1 having been straightened by stretching to a substantially straight shape.

Fig. 3 illustrates an embodiment of a device according to the invention, where the device is in its non-activated state of shape A. More specifically, by covering the stretched and straight shape-changing member 1 in Fig. 2 with a delay means 2, here in the form of a tube 2 having a sufficiently small inner cross section, the stretched shape of the shape-changing member 1 can be maintained even when the device is implanted into a human body and the temperature of the shape-changing member 1 thus exceeds the threshold, e.g. 30°C.

The delay means 2 may be flexible enough to follow the curves in e.g. vessels, but has a stiffness, here especially in its radial direction, which withstands the shape-changing force of the shape-changing member 1. Thus, having been implanted into the human body, the shape-changing member 1 of the device will strive towards its original, here curved, shape according to Fig. 1, but is restrained by the delay means 2.

However, by manufacturing the delay means 2 from a resorbable material, the delay means 2 will be resorbed by time and the shape-changing member 1 will resume its original shape when the delay means 2 has been resorbed to such a degree or extent that it cannot restrain the shape-changing member 1 any longer, as schematically illustrated in Fig. 4. Thus, the device has now "been transformed" from its non-activated long state of shape A (Fig. 3), to an activated, shortened state of shape A' (Fig. 4), where the device consists essentially of the shape-changing member 1 only.

The device in Fig. 3 may be manufactured in the following way. The thread 1 of a shape memory material, e.g. with the shape illustrated in Fig. 2, is programmed to remember the shape illustrated in Fig. 1 by being held in that shape while at the same time being heated to a

temperature above said threshold. Upon cooling the thread 1 beneath the threshold temperature, e.g. down to room temperature, the thread 1 will adopt its previous shape shown in Fig. 2. In this cool state, the thread 1 is  
5 covered by the resorbable tube 2, e.g. by threading the tube 2 onto the thread 1 or by forming the tube 2 around the thread 1.

Other embodiments of a device according to the invention may operate and may be manufactured in a  
10 corresponding manner. Thus, a shape-changing member of a memory material is first held in a "preferred" state of shape while being heated above a threshold temperature, and then cooled beneath the threshold temperature so that it resumes its previous "non-preferred" state of shape.  
15 Thereafter, the now "programmed" shape-changing member is "locked" in said non-preferred state of shape by a delay means in such a way that the delay means will obstruct the shape-changing member from resuming its preferred state of shape when being heated again, e.g. in a human  
20 body.

Referring now again to Fig. 3, the inner radius of the tube 2 must not necessarily be so small that the shape-changing member in the form of the thread 1 cannot move at all in the radial direction. Hence, there may be  
25 a small radial play in which the shape-changing member 1 can move without consequently being able to change the length of the device to any larger extent. However, the device in Fig. 3 may also be manufactured with essentially no play between the shape-changing member 1  
30 and the inner side of the delay means 2, possibly also with a pretension or bias force from the delay means 2 acting on the shape-changing member 1.

In order to clearly illustrate the shortening of the device, the curved thread 1 is located to the left in  
35 Fig. 4, but, after its transformation, the thread 1 may just as well be located anywhere else along the remaining parts of the tube 2.

Figs 5 to 8 show the principle of delayed elongation according to the invention.

In Fig. 5, a shape-changing member 3, here in the form of a thread 3 of a shape-memory material, is shown  
5 having a straight original shape.

Fig. 6 shows the shape-changing thread member 3 of Fig. 5 when having been folded to a curved shape.

Fig. 7 illustrates an embodiment of a device according to the invention comprising a thread as  
10 illustrated in Fig. 6, illustrating the device is in its non-activated state of shape B. By covering the curved shape-changing member 3 with a delay means 4 in the form of a tube 4 of a resorbable material, the curved shape B can be maintained even when the device is implanted into  
15 a human body and strive towards its original straight shape.

As schematically illustrated in Fig. 8, after implantation into the human body, the delay means 4 is resorbed by time and consequently the shape-changing  
20 member 3 will be released to resume its original straight shape B'. Thus, the device has now been transformed from its non-activated short state of shape B (Fig. 7) to an activated, elongated state of shape B' ( Fig. 8).

In the illustrated embodiments, the length of the  
25 shape-changing member 1;3 is substantially unchanged by the transformation, whereas the shape of the shape-changing member 1;3 is changed so that the length of the device is changed.

According to the invention, the material from which  
30 the shape-changing member is formed may consist of or at least include Nitinol, which is an alloy composed of nickel (54-60%) and titanium. Small traces of chrome, cobalt, magnesium and iron may also be present in Nitinol. Alternatively, other materials such as Shape  
35 Memory Polymers (SMP) could be used as the shape memory material.

Actually, as far as the present invention concerns, the shape-changing material does not have to be a shape memory material. Any superelastic material would function in most applications.

5        Examples of usable resorbable materials from which the delay means may be made, or at least include, are PDS (polydioxanon), Pronova (polyhexaflouropropylen-VDF), Maxon (polyglyconat), Dexon (PGA, polyglycolic acid), Vicryl (polyglactin), PLA (polylactic acid), PDLA  
10    (polydexolactic acid), PLLA (pololevolactic acid), starch, different kinds of sugar, butyric acid, collagen, and collatamp. Depending on the choice of material, the release of the shape-changing forces may be delayed for a desired period of time. Also design parameters such as  
15    the thickness of the resorbable material may be set so that the shape-changing forces are delayed as long as desired. The delay time may vary from e.g. a few days up to several years depending on the application.

20        The thickness of the delay means may vary along the device, so that the order in which different parts of the device are released by the delay means may be controlled.

Figs 9 to 20 show some different embodiments of a device according to the invention.

25        Fig. 9 shows an embodiment of a device according to the invention being an alternative arrangement of a device for delayed elongation as compared to the device shown in Fig. 7. Instead of a resorbable tube 4 as in Fig. 7, the resorbable means comprises resorbable crosslinks 6 which hold the shape-changing member 5 in  
30    its curved state of shape and thus the device in its non-activated short state of shape C.

Resorbable crosslinks 6 (Fig. 9) may also be combined with a tube 4 (Fig. 7).

35        Fig. 10 shows an embodiment of a device according to the invention in its non-activated elongate state of shape D. Here, the shape-changing member 7 is scissors-shaped. A delay means 8 in the form of a tube 8 of

resorbable material holds the shape-changing member 7 in a stretched, elongated state of shape and, thus, also the device in its elongate state of shape D. When the delay means 8 has been sufficiently resorbed, the scissors-shaped shape-changing member 7 will resume its original non-stretched shape and the device is transformed to its activated short state of shape D', (Fig. 11).

Fig. 12 shows an embodiment of a device according to the invention in its non-activated short state of shape E. A scissors-shaped shape-changing member 9 of the device is held in a short state of shape by means of a delay means in the form of a resorbable thread 10, and, thereby, the whole device is held in its short state of shape E. When the delay means 10 is cut off by means of resorption, the shape-changing member 9 will resume its original elongate shape so that the device is transformed to its activated state of shape E', (Fig. 13).

Fig. 14 shows an embodiment of a device according to the invention comprising a shape-changing member in the form of a coil 11 of a shape-memory material having been stretched and put in a delay means in the form of a tube 12 of resorbable material. The device is then in its non-activated state of shape F. When the delay means 12 has been sufficiently resorbed, the shape-changing member 11 will resume its original shorter and wider shape as shown in Fig. 16, and the device is transformed to its activated state of shape F'.

In an alternative embodiment shown in Figs 15a and 15b of a device according to the invention, the tube 12 in Fig. 14 is replaced by a resorbable rod 13 provided with grooves 13a in which a coil 11 is initially winded. The winding of the coil 11 in the grooves 13a obstructs the coil 11 from resuming its original shape (Fig. 16) and, hence, the device is held in its non-activated state of shape G by the rod 13, as illustrated in Fig. 15a. By resorption of the rod 13 in e.g. a human body, the shape-changing force of the coil 11 is released and the device

is transformed to its activated state of shape G' as shown in Fig. 16.

In another embodiment shown in Fig. 17 of a device according to the invention, a coil 14 is wound around a resorbable rod 15. When the rod 15 is resorbed, the shape-changing forces of the coil 14 will be released so that the coil 14 resumes an original elongate shape, as shown in Fig. 18, whereby the device is transformed from its non-activated state of shape H to its activated state of shape H'.

Fig. 19 shows an embodiment of a device according to the invention in the form of a patch for closing or obstructing openings, e.g. in the heart of a human or animal body. The patch has a shape-changing member 16 comprising a grid matrix formed by threads made of memory material such as Nitinol or SMP. The threads may be covered individually by biocompatible material such as PTFE or dacron to fill in the gaps between the threads, e.g. in the way shown in Fig. 26 with threads 28 and biocompatible material 29.

The patch in Fig. 19 further comprises a frame 17 for anchoring the patch in the body, e.g. by means of sutures. The frame may be made of any biocompatible material, such as PTFE or dacron. By the use of a cone (not shown), the threads may be spread apart, creating a central opening 16a in the patch. The cone is advanced until a delay means 18 in the form of a separate ring 18 of a resorbable material, initially positioned on the cone, is positioned in the opening 16a. The cone is then drawn back and the ring 18 is left in the opening 16a, restraining the elastic threads in such a way that the central opening 16a in the patch is maintained. Fig. 19 shows the patch in its non-activated state of shape I with the ring 18 positioned centrally. After implant and sufficient resorption of the restraining ring 18 and after a specified period of time, the central opening in the patch is closed and the patch is activated.

Fig. 20 shows an alternative embodiment of a device according to the invention in the form of a patch for closing openings. The patch may be constructed by attaching delay means 19 in the form of resorbable threads or bands 19 to the top of a sharp cone and down along the sides of the cone, advancing the cone through the middle of the patch so that the elastic threads 16 are spread out and thus an opening 16a in the patch is created, and fastening one end of each band to the frame 17 on one side of the patch and the other end of each band 19 to the frame 17 on the other side of the patch, so that each band 19 encircle the opening. The bands 19 could be placed at regular intervals along the circumference of the opening so that they expand a substantially circular hole in the middle of the patch. By means of the resorbable bands 19, the patch is held in its non-activated state of shape J.

It is to be noted that the above-described different embodiments are examples only. There are many possible different forms of a device according to the present invention. For example, the single shape-changing thread in Figs 1 to 9 may be replaced by several threads or by one or more bands. The scissors-shaped members 7 and 9 in Figs 10 to 13 may be multiplied so as to form a scissor-shaped area, which in turn may be shaped into different forms. The single tube in Figs 3, 7, 10 and 14 may be slotted or may be divided into several tube segments. The number of possible designs of a device according to the invention is, in fact, infinitely great.

Next, an embodiment according to the invention of a device for treatment of mitral annulus dilatation will be described.

The device shown in Fig. 21, being in an elongate and non-activated state of shape K, comprises a shape-changing member 20 in the form of a shape memory metal thread 20, a delay means 21 in the form of a resorbable sheath 21 enclosing the shape memory metal thread 20 for



holding it in a straightened state of shape, and self-expandable stents 22 and 23 located at the opposite ends of the device.

5 The device may include one or more additional shape memory metal threads, e.g. if a stronger shortening force is desired.

10 The shape memory metal thread 20 may be made of Nitinol, or other similar material which has a memory of an original shape as illustrated in Fig. 22, and can be temporary forced into another shape, e.g. as illustrated in Fig. 21.

15 The resorbable sheath 21 is made of PDS, but it may also be made of any other material which is resorbable by the surrounding blood and tissue when applied in a human body and has the required stability and bending properties. The thickness of the resorbable sheath 21 is chosen so that the time needed for the surrounding blood and tissue in the coronary sinus 24 to resorb the resorbable sheath 21 enough for the device to enter its  
20 second shorter state of shape K' is adapted to the time needed for the ends of the device to be fixed within the coronary sinus 24.

25 The self-expandable stents 22 and 23 may be of conventional type with an elastic cylindrical unit, made of e.g. Nitinol, in an opened zigzag configuration and a cylindrical elastic film having a diameter substantially the same as of the elastic units.

30 The above-described device, as seen in Fig. 21, is positioned in the coronary sinus 24, shown in Figs 23 to 25, in the following way:

35 An introduction sheath (not shown) of synthetic material may be used to get access to the venous system. Having reached access to the venous system, a long guiding metal wire (not shown) is advanced through the introduction sheath and via the venous system to the coronary sinus 24. This guiding wire is provided with X-

ray distance markers so that the position of the guiding wire in the coronary sinus 24 may be monitored.

The elongate device in Fig. 21 is locked onto a stent insertion device (not shown) so that the self-expandable stents 22 and 23 are held in a non-expanded state. Thereafter, the stent insertion device with the elongate device locked thereon is pushed through the introduction sheath and the venous system to the coronary sinus 24 riding on the guiding wire. After having obtained an exact positioning of the elongate device in the coronary sinus 24, as illustrated in Fig. 23 where the mitral valve annulus 25 and the mitral valve 26 having a central gap 27 is shown, the stent insertion device is removed, whereby the self-expandable stents 22 and 23 will expand against the inner wall of the coronary sinus 24 and provide for a temporary fixation of the elongate device in the coronary sinus 24. Then, the guiding wire and the introduction sheath are removed, the introduction hole is sutured and the operation is finished.

After the operation, the self-expandable stents 22 and 23 will grow into the wall of the coronary sinus 24 while at the same time the resorbable sheath 21 will be resorbed by the surrounding blood and tissue in the coronary sinus 24, as schematically illustrated in Fig. 24. When the resorbable sheath 21 has been resorbed to such a degree that it cannot hold the shape memory metal thread 20 in its straightened state of shape any longer, the self-expandable stents 22 and 23 will be in a fixed state, i.e. being properly fixed into the wall of the coronary sinus 24. Then the shape memory metal thread 20 retracts and the device is transformed to its activated shorter state of shape K', as illustrated in Figs 22 and 25. This shortening of the device makes it bend towards the mitral valve annulus 25, moving the posterior part thereof forward. This movement reduces the

circumference of the mitral valve annulus 25 and thereby closes the central gap 27.

The device may be positioned by catheter technique or by any other adequate technique. It may be designed or  
5 heparin-coated so as to avoid thrombosis in the coronary sinus 24, thus reducing the need for aspirin, ticlopedine or anticoagulant therapy.

Fig. 26 shows one possible arrangement of a part of a contractable area according to the invention. The  
10 contractable area comprises a shape-changing member in the form of a grid matrix of shape memory metal threads 28 covered by a delay means in the form of a fabric of a resorbable material (note that Fig. 26 previously was used to illustrate how the threads of the patches of Figs  
15 19 and 20 may be covered with biocompatible material). The fabric comprises resorbable bands 29 which have been weaved together to form an area. Each of the resorbable bands 29 is solid except for a cylindrical hollow space in which a thread 28 is located, just like the thread 1  
20 is located inside the tube 2 in Fig. 3.

The bands 29 restrains the threads 28 from being folded to their original curved shapes as long as the fabric 29 is not resorbed.

Analogous to the device in Fig. 3, there may be a  
25 radial play between the inner wall of each band 29 and the thread 28 being located inside it, in which play the thread 28 can move without consequently being able to change the size of the area of the device to any larger extent.

30 Further, the hollow space in each band 29 must not necessarily be cylindrical. In fact, if the width of each band 29 is enough small as compared to the curves that the threads 28 will assume when being "activated" as a result of the bands 29 being resorbed, the bands 29 may  
35 be hollow.

The contractable area in Fig. 26 may be manufactured by threading a thread 28 of a memory material into each

resorbable band 29 and then weaving the bands 29 with threads 28 together to form the fabric as illustrated in Fig. 26.

Another possible way of making a contractable area according to the invention would be to arrange threads or bands of a memory material in a grid matrix and to fix the threads or bands together with resorbable crosslinks. The resorbable crosslinks would then restrain the threads or bands from being folded as long as enough much of the resorbable material in the crosslinks is left unresorbed.

A contractable area according to the invention, as the one previously mentioned or as the one shown in Fig. 26, may be formed into a contractable sac as shown in Figs 27 to 30, which sac may be used to support a body organ or to restrain a pathologically growing body organ.

Figs 27 to 30 illustrate the use of a contractable sac 30 for treatment of pathological heart growth, according to another embodiment of the invention.

Referring to Fig. 27, the sac 30 in its non-activated state of shape L is thread inside out on a catheter 31 with an anchoring means 32, here in the form of a suction cup 32, and the catheter 31 with the sac 30 is introduced to the apex cordis 33a of the heart 33 in known manner.

Now referring to Fig. 28, the suction cup 32 is put on apex cordis 33a and the sac 30 is pushed off the catheter 31, by means of a catheter instrument (not shown), over the suction cup 32 and up over the heart 33.

Now referring to Fig. 29, when the sac 30 is positioned round the heart 33, the suction cup 32 is pulled out through the bottom of the sac 30 and the catheter 31 is removed from the body.

After a period of time, the resorbable material of the sac 30 will be resorbed and a restraining force by the shape memory metal threads against the heart 33 is released, hence, the sac 30 is transformed to its activated state of shape L', as illustrated in Fig. 30.

The sac 30 will then press itself tight round the heart 33 and apply a continuous restraining force on the heart 33, thus preventing the heart 33 from growing further.

A contractable area according to the invention can also be used as a contractable sheet for treatment of e.g. alveolar sac growth.

Figs 31 and 32 show the use of an embodiment of a device according to the invention for treatment of alveolar sac growth.

Referring to Fig. 31. a contractable sheet 34 in its non-activated state of shape M is rolled up on a catheter 35 and introduced between ribs 36 via sinus pleurae to the space between pleura pulmonalis and pleura parietalis of the lung 38.

Now referring to Fig. 32, the sheet 34 is then rolled out over the lung 38 and the catheter 35 is removed.

The ends of the sheet 34 are arranged to grow fixed to the pleura pulmonalis so that subsequent contraction of the sheet 34, as a result of the resorbable material of the sheet 34 being resorbed, causes the sheet 34 to compress the lung 38 by means of a force of the shape memory metal threads in the sheet 34. Hence, pathological growth of alveolar sacs is prevented.

In this embodiment the contractable sheet 34 contracts in two directions, one approximately vertical and one approximately horizontal. The sheet 34 could also be designed to contract in one direction only, e.g. the most horizontal one, and still prevent alveolar sacs from growing.

It is to be understood that modifications of the above described devices and methods can be made by people skilled in the art without departing from the spirit and scope of the invention.

35

## CLAIMS

1. A medical device for providing a change of shape  
in a part of the body of an organism, said device  
5 comprising  
a first set of forces working towards a change of  
shape of the device, and  
a second set of forces working for preserving a  
present shape of the device and thereby counteracting  
10 said first set of forces, wherein said first and said  
second set of forces each are inherent in a solid  
material of the device, and wherein forces of said second  
set of forces are arranged to decrease as a result of  
said solid material interacting chemically with said part  
15 of the body.
2. A medical device according to claim 1, wherein  
said second set of forces is inherent in a decomposable  
material.
3. A medical device according to claim 1 or 2,  
20 wherein said forces of said second set of forces are  
arranged to decrease as a result of said solid material  
being decomposed by said part of the body.
4. A medical device according to any one of the  
preceding claims, wherein said second set of forces is  
25 inherent in a resorbable material.
5. A medical device according to any one of the  
preceding claims, wherein said forces of said second set  
of forces are arranged to decrease as a result of said  
solid material being resorbed by said part of the body.
- 30 6. A medical device according to any one of the  
preceding claims, wherein said first set of forces is  
inherent in an elastic material.
7. A medical device according to any one of the  
preceding claims, wherein said first set of forces is  
35 inherent in a material having superelasticity properties.

8. A medical device according to any one of the preceding claims, wherein said first set of forces is inherent in a shape memory material.

5 9. A medical device according to any one of the preceding claims, wherein said first set of forces is inherent in a shape memory metal.

10 10. A medical device according to claim 9, wherein said first set of forces is inherent in a metal comprising Nitinol.

11. A medical device according to any one of claims 1 to 8, wherein said first set of forces is inherent in a shape memory polymer.

12. A medical device according to any one of the preceding claims, wherein the device is arranged to  
15 contract into a new shape as a result of said second set of forces being decreased.

13. A medical device according to any one of claims 1 to 11, wherein the device is arranged to expand into a new shape as a result of said second set of forces being  
20 decreased.

14. A medical device according to any one of the preceding claims, wherein the device is arranged to change its shape in one dimension.

25 15. A medical device according to any one of the preceding claims, wherein the device is arranged to change its shape in two dimensions.

16. A medical device according to any one of the preceding claims, wherein the device is arranged to change its shape in three dimensions.

30 17. A medical device being insertable into the body of an organism, said device comprising

a member (1;3;5;7;9;11;14;16;20;28) having a preferred state of shape towards which the member (1;3;5;7;9;11;14;16;20;28) by means of inherent forces  
35 strive when being in a non-preferred state of shape, and a delay means (2;4;6;8;10;12;13;15;18;19;21;29) having a weakenable inherent stiffness to hold the member

(1;3;5;7;9;11;14;16;20;28) in the non-preferred state of shape a period of time after the device is inserted into the body of the organism.

5 18. A medical device according to claim 17, wherein said delay means (2;4;6;8;10;12;13;15;18;19;21;29) holds said member (1;3;5;7;9;11;14;16;20;28) in a non-preferred state of shape by counteracting the inherent forces of the member (1;3;5;7;9;11;14;16;20;28).

10 19. A medical device according to claim 17 or 18, wherein said delay means (2;4;6;8;10;12;13;15;18;19;21;29) holds said member (1;3;5;7;9;11;14;16;20;28) in a non-preferred state of shape while the inherent stiffness of the delay means (2;4;6;8;10;12;13;15;18;19;21;29) overcomes the inherent forces of the member (1;3;5;7;9;11;14;16;20;28).

20. A medical device according to any one of claims 17 to 19, wherein said delay means (2;4;6;8;10;12;13;15;18;19;21;29) comprises a decomposable material.

20 21. A medical device according to any one of claims 17 to 20, wherein said delay means (2;4;6;8;10;12;13;15;18;19;21;29) comprises a resorbable material.

22. A medical device according to any one of claims 17 to 21, wherein said member (1;3;5;7;9;11;14;16;20;28) comprises an elastic material.

25 23. A medical device according to any one of claims 17 to 22, wherein said member (1;3;5;7;9;11;14;16;20;28) comprises a material having superelasticity properties.

30 24. A medical device according to any one of claims 17 to 23, wherein said member (1;3;5;7;9;11;14;16;20;28) comprises a shape memory material.

25. A medical device according to any one of claims 17 to 24, wherein said member (1;3;5;7;9;11;14;16;20;28) comprises Nitinol.

35 26. A medical device being insertable into the body of an organism, said device comprising

a member (1;3;5;7;9;11;14;16;20;28) having a preferred state of shape and having a tendency to



transfer its shape towards said preferred state of shape when being in a non-preferred state of shape, and

a resorbable means (2;4;6;8;10;12;13;15;18;19;21;29) being arranged to hold the member (1;3;5;7;9;11;14;16;20; 5 28) in the non-preferred state of shape and to delay the transfer when the device is inserted into the body of the organism by counteracting said transfer during resorption of the resorbable means (2;4;6;8;10;12;13;15;18;19;21;29) by the surrounding body of the organism.

10 27. A medical device according to claim 26, wherein said member (1;3;5;7;9;11;14;16;20;28) comprises an elastic material.

28. A medical device according to claim 26 or 27, wherein said member (1;3;5;7;9;11;14;16;20;28) comprises 15 a material having superelasticity properties.

29. A medical device according to any one of claims 26 to 28, wherein said member (1;3;5;7;9;11;14;16;20;28) comprises a shape memory material.

30. A medical device according to any one of claims 20 26 to 29, wherein said member (1;3;5;7;9;11;14;16;20;28) comprises Nitinol.

31. A device for reshaping a body vessel (24), said device being elongate and having such dimensions as to be insertable into the vessel (24) and having two states, in 25 a first state (K) of which the device has a shape that is adaptable to the shape of the vessel (24), and to the second state (K') of which the device is transferable from said first state (K), said device comprising

a fixing means (22, 23) for fixing the ends of the 30 device within the vessel (24), when the device is first positioned therein,

a member (20) for transferring the device to the second state (K') by reshaping it, and

a resorbable means (21) for delaying said reshaping 35 until the ends of the device are fixed by keeping said device in said first state (K) until the resorbable means (21) is resorbed.

32. The device according to claim 31, wherein said resorbable means (21) comprises a resorbable sheath being arranged to enclose said member (20).

33. The device according to claim 31 or 32, wherein  
5 said fixing means (22, 23) is arranged to expand against the wall of the vessel (24) when first positioned therein.

34. The device according to any one of claims 31 to 33, wherein said fixing means (22, 23) is arranged to  
10 grow into the wall of the vessel (24).

35. The device according to any one of claims 31 to 34, wherein said fixing means (22, 23) comprises a self-expandable stent at each end of the device.

36. The device according to any one of claims 31 to  
15 35, wherein said member (20) comprises a shape memory material providing said reshaping of the device.

37. The device according to claim 36, wherein said member (20) comprises Nitinol providing said reshaping of the device.

20 38. The device according to any one of claims 31 to 37, wherein said reshaping of the device comprises shortening of the device.

39. The device according to any one of claims 31 to 39, wherein said device is used for treatment of mitral  
25 annulus dilatation.

40. The device according to claim 39, wherein said vessel (24) is the coronary sinus.

41. The device according to claim 40, wherein said reshaping of the device is used for reducing the radius  
30 of curvature of the coronary sinus (24).

42. A method for reshaping a body vessel (24),  
comprising the steps of  
inserting an elongate device into the vessel (24),  
fixing the ends of the device within the vessel  
35 (24),  
reshaping the device, and

delaying said reshaping by a resorbable means (21) so that the step of fixing the ends of the device is performed before the step of reshaping the device.

43. The method according to claim 42, wherein said  
5 step of fixing the ends of the device comprises providing a growth of the ends into the wall of the vessel (24).

44. The method according to claim 42 or 43, wherein a shape memory material is used in the device for said step of reshaping the device.

10 45. The method according to claim 44, wherein Nitinol is used in the device for said step of reshaping the device.

46. The method according to any one of claims 42 to 45, wherein said step of reshaping the device comprises  
15 the step of shortening the device.

47. The method according to any one of claims 42 to 46, wherein the method is used for treatment of mitral annulus dilatation.

48. The method according to claim 47, wherein said  
20 device is inserted into the coronary sinus (24) in the vicinity of the posterior leaflet of the mitral valve (26).

49. The method according to claim 48, wherein said reshaping is used for reducing the curvature of the  
25 coronary sinus (24) and thereby reducing the radius of circumference of the mitral valve annulus (25).

50. A device for restraining growth of a body organ (32;34) of an organism, said device being implantable into the body of the organism and comprising  
30 an elastic contractable member being arranged to enclose said body organ (32;34), and

a resorbable means being arranged to delay contraction of the contractable member when the device is implanted in the body of the organism by counteracting  
35 the contraction during resorption of the resorbable means by the surrounding body of the organism.

51. A device according to claim 50, wherein said contractable member comprises a shape memory material.

52. A device according to claim 51, wherein said contractable member comprises Nitinol.

5 53. A method for restraining growth of a body organ (32;34) of an organism, comprising the steps of inserting a restraining device into the body of the organism,

10 enclosing the body organ (32;34) with the restraining device, compressing said restraining device by means of a contractable member of said restraining device, and delaying said compression by a resorbable means.

15 54. A method according to claim 53, wherein the method is used for treatment of pathological heart growth.

55. A method according to claim 53, wherein the method is used for treatment of alveolar sac growth.

20 56. A method according to claim 53, wherein the method is used for treatment of bullous emphysema.

p  
a  
v  
0  
2  
0  
1  
1  
m

## ABSTRACT

5 A medical device and a method for providing a change  
of shape in a part of the body of an organism. The device  
is insertable into the body of the organism and comprises  
a member (1;3;5;7;9;11;14;16;20;28) having a preferred  
state of shape and having a tendency to transfer its  
shape towards said preferred state of shape when being in  
10 a non-preferred state of shape. The device further  
comprises a resorbable means (2;4;6;8;10;12;13;15;18;19;  
21;29) which is arranged to hold the member (1;3;5;7;9;  
11;14;16;20;28) in the non-preferred state of shape and  
to delay the transfer when the device is inserted into  
15 the body of the organism by counteracting said transfer  
during resorption of the resorbable means (2;4;6;8;10;12;  
13;15;18;19;21;29) by the surrounding body of the  
organism.

The device and method can for example be used for  
20 treatment of mitral annulus dilatation and particularly  
for reducing the circumference of the mitral valve  
annulus. The device and method can further be used for  
treatment of pathological heart growth, for treatment of  
alveolar sac growth and for treatment of bullous  
25 emphysema.

30

35

To be published:  
Figs 3 and 4 in combination




Fig. 1




Fig. 2




Fig. 3




Fig. 4



Fig. 5




Fig. 6




Fig. 7

















Fig. 8












Fig. 21




Fig. 22




Fig. 23




Fig. 24




Fig. 25




Fig. 26





Fig. 27




Fig. 28





Fig. 29




Fig. 30




Fig. 31




Fig. 32

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**